

7. Optical interference coating comprising interleaved thin-film stacks
EPB 97-28 0565703 NDN- 069-0322-9094-0

INVENTOR(S)- GASLOLI, Paul, J. 89 Hovey Street Watertown, MA 02172 US

PATENT ASSIGNEE(S)- OSRAM SYLVANIA INC. (286495) 100 Endicott Street Danvers, MA 01923
US DESG. COUNTRIES- BE; DE; FR; GB; NL
PATENT NUMBER- 00565703/EP B1

PATENT APPLICATION NUMBER- 92924118

DATE FILED- 1992-10-26

PUBLICATION DATE- 1997-07-09

AVAILABILITY LIMITER- WIPO Document

PATENT PRIORITY INFO- US, 787855, 1991-11-05

ATTORNEY, AGENT, OR FIRM- Butler, Michael John, (29061), Frank B. Dehn & Co., European Patent Attorneys, 179 Queen Victoria Street, London EC4V 4EL, GB

INTERNATIONAL PATENT CLASS- G02B00528

PCT APP. NO.- 9209050/US/PCT

PCT PUB. NO.- 93009449/WO

PCT PUB. DATE- 1993-05-13

PUBLICATION- 1993-10-20, A1, Published application with search report; 1997-07-09, B1, Publication of granted patent

FILING LANGUAGE- English

PROCEDURE LANGUAGE- English

LANGUAGE- English

EXEMPLARY CLAIMS- An optical interference coating for reflecting infrared radiation and transmitting visible light comprising:

one or more interleaved stacks said interleaved stacks comprising a first stack containing three alternating layers of high and low refractive index materials of form (L/a bH L/a), and a second stack containing three alternating layers of high and low refractive index materials of the form (H/a bL H/a);

wherein L and H are a low and a high index of refraction material respectively, L and H each being defined as having an optical thickness of a multiple of a quarter-wave of the stack wavelength; and wherein a and b are predetermined values in the ranges of:

1.75 (less than) a (less than) 2.5 and 2.75 (less than) b (less than) 3.25.

A coating as claimed in claim 1, further comprising a stack of the form (L/a bH L/a) added to one side of the one or more interleaved stacks to achieve symmetry.

A coating as claimed in claim 1 or 2, further comprising one or more stacks of the form (L/2 H L/2) added to the one or more interleaved stacks to define the transmission bandwidth for an IR reflector.

A coating as claimed in claims 1, 2 or 3, wherein the low refractive index material has a value of between approximately 1.40-1.50 and the high index of refraction material has a value of between approximately 2.0-2.2.